

# TPS<sup>®</sup> COURT SURFACES

## TPS<sup>®</sup> 5000 COLOR CONCENTRATE

### DESCRIPTION

---

TPS<sup>®</sup> 5000 Color is heavy bodied, multi-purpose acrylic latex coating fortified with mineral fillers, fibers and high quality pigments for a long-lasting, attractive recreational surface. TPS 5000 Color can be used for a “non-textured” as well as a textured coat containing sand. It is supplied in concentrated form and is diluted with water prior to application. TPS Color comes in nine vibrant colors: meadow green, forest green, brick red, terra cotta, tan, adobe, turquoise, cobalt blue and grey.

### USES

---

TPS 5000 Color is used as a colored surface on asphalt and concrete pavements for new and existing tennis courts, playgrounds and multi-purpose areas. On-the-job mixing allows improved filling characteristics, simply by adding sand to the mixture.

### SURFACE PREPARATION

---

New asphalt pavements should cure a minimum of 14 days, and concrete should cure a minimum of 28 days prior to any coating application. When installing over concrete surfaces, the concrete should be installed without curing compound. New and old surfaces should be thoroughly cleaned to be free from oil, grease, dirt and other foreign matter.

### MIX DESIGN TEXTURED COAT

---

The following mix is recommended for regular pavement conditions. More sand can be added if better filling is required.

TPS 5000 Color	50 gallons
Dry Silica Sand (30 to 90 mesh)	300-400 lbs.
Water	25-30 gallons

When ordering TPS 5000 Asphalt Surfer, figure 14-20 square yards per gallon of concentrated material for each coat depending on sand mesh size and condition of substrate.

### MIX DESIGN – NON-TEXTURED

---

TPS 5000 Color should be mixed 2 parts concentrated material to 1 part water. When ordering TPS 5000 Color, figure 24-26 square yards per gallon of concentrated material for each non-textured coat.

### APPLICATION

---

TPS 5000 Color is applied with a rubber bladed squeegee. Care should be taken not to leave ridges.

### CLEAN-UP

---

Rinse tools with water soon after using.

### SHELF LIFE

---

Approximately 12 months.

### PHYSICAL PROPERTIES

---

Weight/Gallon	9.7 lbs. per gallon
Drying Time	30 to 60 minutes
Ready to Play	24 hours

### PRECAUTIONS & LIMITATIONS

---

Keep from freezing. Harmful if swallowed. Read material safety data sheets.

This product will not prevent pavement cracks from occurring or re-occurring. Do not apply if surface temperature is less than 50F or more than 140F. Do not apply over tar emulsion sealers. Apply only when ambient temperature is 50F and rising. Do not apply when rain is imminent.

## SHIPPING WEIGHT

---

50 gallon drum	520 lbs.
5 gallon pail	54 lbs.

Limited Warranty: This product is guaranteed to be of the kind and quality described in its specifications. All other warranties are specifically excluded and the manufacturer shall not be liable for any consequential damages. Under no circumstances shall the manufacturer's liability exceed the purchase price of any materials deemed to be defective under this warranty. Warranty will be voided on multi-coated applications if material made by other manufacturers that has not been approved by the manufacturer of TPS 5000 products, is used with this product.



### HELLAS CONSTRUCTION, INC.

12710 Research Boulevard Suite 240

Austin, Texas 78759

T: 512.250.2910

F: 512.250.2910

[WWW.HELLASCONSTRUCTION.COM](http://WWW.HELLASCONSTRUCTION.COM)

